



Mandals Antistatica is an electrically conductive hose for transfer of fuels and other flammable liquids.

Mandals Antistatica is used for transfer of fuels and other flammable liquids. The hose can also be used in the construction and general industry.

Mandals Antistatica is made from a blend of nitrile rubber and PVC, with added UV barrier to prevent damage from UV radiation. The nitrile rubber blend has additives making the hose itself electrically conductive, ensuring a volume resistivity of max. $10^6 \text{ Ohm} \cdot \text{cm}$.

This method of achieving conductivity removes the risk of breaking conductive wires commonly used in rubber hoses for this purpose.

The rubber blend is extruded through a circular woven reinforcement made from filament polyester yarn. This production method gives a very strong bonding between cover and lining as well as firmly encapsulating the reinforcing polyester. The hose has high resistance against commonly used chemicals.

Because of the interlocking circular weave, the hose does not stretch when pulled. For the same reason, it has a very high pressure rating to wall thickness ratio.

It can operate from -30°C to $+75^\circ\text{C}$.
Intermittent use up to $+80^\circ\text{C}$.

Mandals Antistatica

Inner Diameter		Wall Thickness		Weight		Burst Pressure		Tensile Strength*	
inch	mm	inch	mm	lbs/ft	kg/m	psi	bar	lbs	kg
3/4	20,0 +1,6	0,09	2,3	0,14	0,21	1500	100	4 200	1 900
1	25,4 +1,6	0,10	2,5	0,18	0,28	1500	100	5 100	2 300
1 1/2	38,0 +1,6	0,09	2,2	0,20	0,30	800	55	6 400	2 900
2	51,0 +2,0	0,09	2,2	0,25	0,38	650	45	8 350	3 800
2 1/2	65,0 +2,0	0,09	2,2	0,35	0,53	650	45	9 200	4 200
3	76,0 +2,0	0,12	3,1	0,64	0,95	725	50	17 800	8 100
4	102,0 +2,5	0,13	3,3	0,90	1,35	550	38	22 450	10 200
5	127,0 +3,0	0,13	3,3	1,14	1,70	435	30	26 850	12 200
6	150,0 +3,0	0,12	3,0	1,14	1,70	525	36	35 400	16 100

To obtain maximum lifetime for the hose, it is recommended that actual Working Pressure and/or Working Tensile Stress do not exceed 1/3 of the above listed values.

* Total theoretical longitudinal strength.