

CHEMICAL RESISTANCE

A-B

	EPDM	Nitrile	Urethan
acetaldehyde 50%	G	X	X
acetic acid. Glacial	G	C	X
acetic acid 30%	G	G	X
acetic anhydride	C	C	X
acetone	G	X	X
acetyl chloride	X	X	X
acetylene	G	E	X
adipic acid	G	E	I
aluminum acetate	G	G	X
aluminum chloride	G	E	C
aluminum fluoride	G	E	C
aluminum hydroxide	I	I	I
aluminum nitrate	G	E	C
aluminum sulfate	G	E	X
ammonia anhydrous	Use anhydrous ammonia hose only		
ammonia gas (cold)	G	E	C
ammonia gas (hot)	C	X	X
ammonium carbonate	G	X	X
ammonium chloride	G	E	E
ammonium hydroxide	G	G	X
ammonium nitrate	G	E	X
ammonium nitrite	G	E	I
ammonium phosphate	G	E	I
ammonium sulfate	G	E	E
amly acetate	X	X	X
amyl alcohol	G	G	X
aniline	G	X	X
aniline dyes	G	X	X
aniline hydrochloride	C	G	X
animal fats	C	E	E
arsenic acid	G	E	C
arsenic trichloride	X	E	I
asphalt	I	G	G
barium chloride	G	E	E

barium chloride	G	E	E
barium sulfate	G	E	E
barium sulfide	G	E	E
beer	G	E	G
benzene	X	X	X
benzoic acid	X	C	I
benzyl alcohol	G	X	X
benzyl benzoate	C	X	I
benzyl chloride	X	X	X
boric acid	G	E	E
brine	G	E	G
bromine-anhydrous	X	X	X
bromine trifluoride	X	X	X
bromine water	G	X	X
bromotoluene	X	X	I
bunker oil	X	E	G
butadiene	X	X	X
butane	X	E	E
butter	G	E	E
butyl acetate	X	X	X
butyl alcohol	C	E	X
butyl aldehyde	C	X	I
butyl amine	G	C	X
butyl benzoate	C	X	I
butyl cellosolve	G	C	X
butyl stearate	X	G	I