

CHEMICAL RESISTANCE

E-F

	EPDM	Nitrile	Urethan
ethane	X	E	C
ethanolamine	G	G	C
ethyl acetate	G	X	X
ethyl acetoacetate	G	X	X
ethyl alcohol (ethanol)	G	E	X
ethyl benzene	X	X	X
ethyl benzoate	G	X	X
ethyl cellulose	C	G	G
ethyl chloride	X	E	C
ethyl ether	X	C	C
ethyl formate	C	X	I
ethyl pentochloro-benzene	X	X	C
ethyl silicate	G	E	I
ethylene	C	E	I
ethylene chloride	X	X	X
ethylene chlorohydrin	C	X	X
ethylene diamine	G	E	X
ethylene dichloride	X	X	X
ethylene glycol	G	E	C
ethylene trichloride	X	X	X
fatty acids	X	G	E
ferric chloride	G	E	E
ferric nitrate	G	E	E
ferric sulfate	G	E	E
fish oil	X	E	I
fluoroboric acid	G	E	I
fluorobenzene	X	X	I
fluorolube	G	E	I
fluosilicic acid	C	E	I
formaldehyde	G	C	X
formic acid	G	G	X
freon, all types	Use freon hoses only		
fuel oil	X	E	G
furfural	G	X	C