

CHEMICAL RESISTANCE

N-P

	EPDM	Nitrile	Urethan
naphtha	X	G	C
naphthalene	X	X	G
naphthenic acid	X	G	I
natural gas	X	E	G
nickel acetate	G	G	X
nickel chloride	G	E	C
nickel sulfate	G	E	C
nitric acid-conc.	G	X	X
nitric acid-dilute	G	X	C
nitrobenzene	G	X	X
nitroethane	C	X	X
nitromethane	C	X	I
nitrogen	G	E	E
nitrous oxide	I	E	I
octachlorotoluene	X	X	X
octyl alcohol	X	G	X
oleic acid	X	C	G
oleum	G	G	C
olive oil	C	E	E
o-dichlorobenzene	X	X	I
oxalic acid	G	G	I
oxygen	G	G	E
ozone	G	X	E
palmitic acid	C	E	E
peanut oil	X	E	G
perchloric acid	C	X	X
perchloroethylene	X	G	X
petroleum	X	E	G
phenol (carbolic acid)	G	X	C
phenylbezene	X	X	I
phenyl hydrazine	C	X	I
phorone	X	X	I
phosphoric acid-20%	G	G	E
phosphoric acid-80%	G	X	I
phosphoric thrichloride	G	X	I
picric acid	G	G	G
pine oil	X	E	I

polyvinyl acetate emulsion	G	I	I
potassium acetate	G	G	X
potassium chloride	G	E	E
potassium cupro cyanide	E	E	E
potassium cyanide	G	E	E
potassium dichromate	G	E	G
potassium hydroxide	G	G	X
potassium nitrate	G	E	E
potassium sulfate	G	E	E
propane	X	E	C
propyl acetate	C	X	I
propyl alcohol (propanol)	G	E	X
propyl nitrate	G	X	I
propylene	X	X	X
pyranol (transformer oil)	X	X	G
pyridine	G	X	G