

CHEMICAL RESISTANCE

S-Z

	EPDM	Nitrile	Urethan
salammoniac	G	E	E
salicylic acid	G	G	I
salt water	G	E	E
sewage	G	E	X
silicone greases	G	E	E
silicone oils	G	E	E
silver nitrate	G	G	E
skydrol 500 & 7000	G	X	X
soap solutions	G	E	C
soap ash	G	E	E
sodium acetate	G	G	X
sodium bicarbonate	G	E	E
sodium bisulfite	G	E	E
sodium borate	G	E	E
sodium chloride (brine)	G	E	E
sodium cyanide	G	E	E
sodium hydroxide	G	G	X
sodium hypochlorite	C	G	X
sodium metaphosphate	G	E	I
sodium nitrate	G	G	E
sodium perborate	G	G	I
sodium peroxide	G	G	X
sodium phosphate	G	E	E
sodium silicate	G	E	E
sodium sulfate	G	E	E
sodium thiosulfate	G	G	E
soybean oil	X	E	G
stannic chloride	G	E	I
stearic acid	G	G	E
styrene	X	X	C
sucrose solution	G	E	X
sulfur	G	X	I
sulfur chloride	X	C	I
sulfur dioxide-dry	E	X	I
sulfur dioxide-liquid	G	X	I
sulfur dioxide-wet	E	X	I
sulfuric trioxide	C	X	I

sulfuric acid 10%	G	C	C
sulfuric acid 10-75%	G	X	X
sulfurous acid	G	G	X
tannic acid	G	E	E
tar bituminous	X	G	I
tartaric acid	C	E	E
terpeneol	X	G	G
tertiary butyl alcohol	C	G	X
tetrachloroethylene	X	X	X
tetraethyl lead	X	G	I
toluene	X	X	X
toluol	X	X	I
transformer oil	X	E	E
transmission fluid A	X	E	E
trichloroethane	X	X	X
trichloroacetic acid	C	G	I
trichloroethylene	X	X	X
tricresyl phosphate	X	X	C
triethanol amine	G	G	X
trinitrotoluene	X	X	I
turbine oil	X	G	E
turpentine	X	E	X
vegetable oils	X	E	G
vinegar	G	G	X
vinyl chloride	X	X	X
water	G	E	G
whiskey, wine	G	E	G
white oil	X	E	E
wood oil	X	E	C
xylene	X	X	X
zinc chloride	G	E	E
zinc sulfate	G	E	I