

CHEMICAL RESISTANCE

C-D

	EPDM	Nitrile	Urethan
calcium acetate	G	G	X
calcium bisulfite	X	X	E
calcium carbonate	E	E	I
calcium chloride	G	E	E
calcium hydroxide	G	E	E
calcium hypochlorite	G	G	X
calcium nitrate	G	E	E
calcium sulfide	G	E	E
carbitol	C	G	X
carbolic acid (phenol)	C	X	C
carbon bisulfite	X	C	I
carbon dioxide	C	E	E
carbonic acid	G	G	E
carbon monoxide	G	E	E
carbon tetrachloride	X	C	X
carbon tetrafluoride	I	I	E
castor oil	C	E	E
caustic soda (sodium hydroxide)	G	G	C
cellosolve	C	X	I
cellosolve acetate	C	X	X
chlorine (dry)	X	X	X
chlorine (wet)	X	X	X
chlorine dioxide	X	X	X
chloroacetone	G	X	X
chloroacetic acid	G	X	X
chlorobenzene	X	X	X
chlorobutadiene	X	X	X
chloroform	X	X	X
chlorotoluenen	X	X	X
chrome plating solutions	C	X	I
chromic acid	G	X	X
citric acid	G	E	G
cobalt	G	E	I
coconut oil	X	E	G
cod liver oil	G	E	E
coke oven gas	X	X	X
copper acetate	G	G	X

copper chloride	G	E	E
copper cyanide	G	E	E
copper sulfate	G	E	E
corn oil	X	E	E
cottonseed oil	C	E	E
creosote (coal tar)	X	E	X
cresol	X	X	X
creylic acid	X	X	X
cumene	X	X	I
cyclohexane	X	E	G
cyclohexanol	X	C	I
cyclohexanone	G	X	X
p-cymene	X	X	I
decalin	X	X	I
denatured alcohol	G	E	X
detergent solution	G	E	C
(non-hydrocarbon) diacetone	G	X	X
diacetone alcohol	G	X	X
dibenzyl ether	C	X	G
dibutyl amine	G	X	X
dibutyl ether	X	X	G
dibutyl phthalate	C	X	C
dibutyl sebecate	C	X	X
dichlorobezene	X	X	X
dichloroethylene	X	X	X
dichloro-isopropyl ether	X	X	G
diesel oil	X	E	C
diethylamine	G	G	C
diethylamine bezene	X	X	X
diethyl ether	X	X	G
diethylene glycol	G	E	X
diethyl sebecate	C	G	I
diisobutylene	G	G	I
diisopropyl bezene	X	X	I
diisopropyl ketone	G	X	X
dimethyl formamide	G	G	I
dimethyl phthalate	G	X	I
dinitrotoluene	X	X	I
dioctyl phthalate	C	C	I
dioctyl sebecate	C	X	I
dipentene	X	G	I
diphenyl – (phenylbezene)	X	X	I
dowtherm oil	X	X	C
dry cleaning fluids	X	C	X